

Exaton 24.13.LR



Exaton 24.13.LR is a high alloyed chromium-nickel covered electrode with rutile coating for welding of dissimilar joints between stainless steel and mild or low alloyed steels. It is also used to create buffer layers with a composition of 18%Cr/8%Ni before overlay alloys are deposited.

The electrode has excellent arc stability, low spatter and fast burn off rate with minimal stub loss. It is also characterized by improved moisture resistance, self peeling slag, high resistance to porosity and easy post weld finishing. It provides smooth uniform beads and works in any standard weld position.

Typical applications include welding of stainless steel to low alloyed steels, buffer layers on low alloy steels before overlays with 304 composition, welding of stainless steels of 23%Cr/12%Ni type, joining of ferritic/martensitic stainless steels of 12-18%Cr type.

Классификации	SFA/AWS A5.4 : E309L-17 EN ISO 3581-A : E 23 12 L R 3 2 Werkstoffnummer : 1.4332
Одобрения	CE EN 13479

Одобрения на материалы выдаются с привязкой к заводу изготовителю. Подробную информацию можно получить в представительствах ESAB.

Сварочный ток	DC+, AC
Содержание ферритной фазы	FN 10-18
Тип сплава	Austenitic CrNi
Тип покрытия	Acid Rutile

Механические свойства при растяжении

Состояние	Предел текучести	Предел прочности при растяжении	Удлинение
ISO			
После сварки	480 MPa	560 MPa	35 %

Типичные свойства образца с V-образным надрезом по Шарпи

Состояние	Температура испытания	Работа удара
ISO		
После сварки	20 °C	55 J
После сварки	-20 °C	45 J

Хим. состав наплавленного металла

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	FN WRC-92
0.02	0.8	1	0.014	0.021	12.5	23	0.06	0.046	14

Данные наплавки

Диаметр	Ток	V	Кол-во электродов/кг наплавл. Металла	Fusion time per electrode at 90% I max	КПД, %	Производительность наплавки при токе 90% от максимального
2.5 x 300.0 mm	45-90 A	28 V	85	38 sec	60 %	1.1 kg/h
3.2 x 350.0 mm	65-120 A	29 V	45	51 sec	60 %	1.6 kg/h
4.0 x 350.0 mm	85-180 A	31 V	29	51 sec	60 %	2.5 kg/h
5.0 x 350.0 mm	110-250 A	32 V	19	58 sec	60 %	3.3 kg/h