

## Exaton 24.13.LNb

Exaton 24.13.LNb is a niobium-stabilized overalloyed filler metal suitable for overlay welding of carbon and low alloy steels, where a type 347 of overlay is required. It is used for Submerged Arc Welding and recommended flux is Exaton 15W..

<b>Классификация сварочной проволоки</b>	SFA/AWS A5.9 : ER"309LNb" EN ISO 14343-A : S 23 12 Nb
--	--

### Хим. состав проволоки

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
0.01	2.1	0.3	0.001	0.013	12.5	24	0.02	0.01	0.05

### Хим. состав проволоки

Nb	Ti	Co
0.8	0.005	0.02