

## Exaton 22.11.L

Exaton 22.11.L is a chromium-nickel strip electrode used for electro-slag welding (ESW) to deposit a single layer overlay of corrosion resistant alloy of 19%Cr/9%Ni composition on carbon- and low alloyed steels. It can also be combined with 19.9.L for surfacing of two layer overlays.

<b>Классификации</b>	SFA/AWS A5.9 : EQ(309L) EN ISO 14343-A : B 22 11 L
----------------------	---

<b>Хим. состав проволоки</b>									
<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>S</b>	<b>P</b>	<b>Ni</b>	<b>Cr</b>	<b>Mo</b>	<b>Cu</b>	<b>Ferrite FN</b>
<=0.015	1.8	0.2	<=0.020	<=0.020	11.5	21	<=0.3	<=0.1	13